



# HI-DRO 60-01 ACRYLIC SHEEN TOP COAT

TECHNICAL DATA SHEET

## PRODUCT DESCRIPTION

**Hi-Dro 60-01 Acrylic Sheen Top Coat** is a one-pack, high performance, water-based acrylic finish coat, specially formulated with enhanced anti-algae and anti-streak marks performance.

## INTENDED USE

It is designed for use over a suitable primer and intermediate in a wide range of environments, including offshore structures, bridges, sport stadia, refineries, petrochemical and chemical plants.

- Enhanced resistance to fungal and algal growth
- Enhanced anti-streak marks property keeping the façade clean
- Excellent weather durability under local climatic conditions
- Good adhesion on stable surfaces
- Easy application with good levelling property

## GENERAL PROPERTIES

<b>Colour</b>	: Wide range of colours
<b>Gloss Level</b>	: Low Sheen
<b>Volume Solids, %</b>	: 38 ± 2 %
<b>Specific Gravity</b>	: 1.34 – 1.38 kg/l (Depending on colours)
<b>Flash point</b>	: >100°C
<b>VOC</b>	: 67 g/L (EPA Method 24)
<b>Typical Thickness</b>	: 40 – 60 µm dry film : 105 – 158 µm wet film

## SURFACE PREPARATION

All surfaces should be clean dry, and free from contamination. The surface should be assessed and treated in accordance with ISO 8504. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

### Damaged Area

Damage area should be prepared with abrasive blast cleaning to Sa 2½ (ISO 8501-1:2007). When abrasive blasting is not possible, mechanical cleaning to St 3 (ISO 8501-1:2007) is acceptable. After the surface preparation, patch primer prior to the application of Hi-Dro 60-01 Acrylic Sheen Top Coat.

Hi-Dro 60-01 Acrylic Sheen Top Coat should always be applied over a recommended anti-corrosive coating scheme for metal surface. The primer surface should be dry and free from all contamination and Hi-Dro 60-01 must be applied within the overcoating intervals specified (refer to application section for details).

### Other Surfaces

The coating may be used on other substrates. Please contact your local Nippon Paint office for more information.



# HI-DRO 60-01 ACRYLIC SHEEN TOP COAT

## TECHNICAL DATA SHEET

### CONDITION DURING APPLICATION

Avoid paint application when the temperature is below 10°C and relative humidity is above 75%, otherwise drying and overcoating times will severely extended. The temperature of steel surface must be minimum 3°C above dew point of surrounding air.

The application should not fall below minimum film forming temperature of the coating. Poor ventilation will result in poor film coalescence and a powdery cracked film which will require removal and re-application.

### APPLICATION GUIDE

<b>Mixing</b>	: Mixed thoroughly before use with a power agitator.
<b>Theoretical Coverage</b>	: 9.5 m <sup>2</sup> /litre at 40 µm DFT 6.3 m <sup>2</sup> /litre at 60 µm DFT
<b>Thinner</b>	: Clean portable water Ready for use, if necessary, dilution should not be more than 5% water

### APPLICATION METHOD

Air and Airless spray are recommended for application. Brush and roller are recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.

### APPLICATION DETAILS

<b>Airless Spray</b>	: Tip Size	: 0.015" – 0.021"
	: Pressure at nozzle	: > 150 kg/cm <sup>2</sup>
<b>Typical Thickness</b>	: 40 – 60 µm dry film	
	: 105 – 158 µm wet film	
<b>Drying Time</b>	: Substrate Temperature	30 °C
	: Surface Dry	1 hrs
	: Through Dry	4 hrs
	: Dry to recoat (min)	4 hrs
	: Dry to recoat (max)*	Extended

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.



# HI-DRO 60-01 ACRYLIC SHEEN TOP COAT

## TECHNICAL DATA SHEET

\* Where an “extended” overcoating time is stated, consult Nippon Paint Protective Coatings for recommended surface preparation to achieve optimal intercoat adhesion.

### RECOMMENDED PAINTING SYSTEM

The following coating systems are recommended for Hi-Dro 60-01 Acrylic Sheen Top Coat:

#### Primer:

- Hi-Pon 20-01 Epoxy Primer
- Hi-Pon 20-03 Epoxy Red Oxide Primer
- Hi-Pon 20-04 STE 80
- Hi-Pon 20-04 STE IM 80
- Hi-Pon 20-07 Epoxy Zinc Phosphate 70
- Hi-Pon 20-10 Epoxy Zinc Phosphate 63
- Hi-Dro 63-01 Universal Epoxy

#### Intermediate:

- Hi-Pon 20-04 STE 80
- Hi-Pon 20-04 STE IM 80
- Hi-Pon 30-02 Epoxy MIO 80
- Hi-Pon 30-03 Epoxy Midcoat 80
- Talkalitt S100

For the choice of coating system for different application, refer to the product brochure or contact Nippon Paint for professional recommendation.

### PACKAGING

Unit	Vol	Container Size
5 L	5 L	5 L
20 L	20 L	20 L

### STORAGE

**Shelf life** : 24 months (25°C)

Subject to re-inspection thereafter. Higher temperature during storage may reduce the shelf life and may lead to gelling in the tin. Frequent temperature cycles may also shorten the shelf life.

Store in tightly closed container in a dry, cool and well ventilated space, keep away from sources of heat and ignition.

### SAFETY PRECAUTION

- This product is intended for use by professional applicators. Refer to the safety information display on the container and in the safety data sheet (SDS) before using the product.



# HI-DRO 60-01 ACRYLIC SHEEN TOP COAT

TECHNICAL DATA SHEET

- Use this product in well-ventilated area, avoid skin contact, spillage on the skin should immediately be removed with suitable cleanser, soap and water.
- Eye should be well flush with water and seek for medical attention immediately upon contact with this product.
- During the application, naked flame, welding operation and smoking is not allowed. Adequate ventilation should be provided.
- If you have any doubt regarding the suitability of use, refer to Nippon Paint for further advice.

## DISCLAIMER

The information in this data sheet is given to the best of Nippon Paint's knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. The condition of the substrate and application are not within Nippon Paint's control. Therefore no implied conditions, warranties or other terms will apply to the Product. Nippon Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint's policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user's responsibility to check with Nippon Paint for the latest version of this data sheet. This data sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail.